

BAKERLOK™

Fast Cure BAKERLOK Thread-Locking Compound replaces welding for casing joints on the bottom lengths to prevent unscrewing while drilling out cement. Welding of shoes, couplings, and collars to casing often weakens the casing and should be avoided wherever possible.



Features/Advantages

Withstanding High Breakout Torque - Tests under bottom hole temperatures ranging from 50° through 400° F showed BAKERLOK withstood greater torque than a standard joint welded in three places with 2 inch beads.

Unaffected by Vibration - At 400° F BAKERLOK was subjected to a steady breakout torque for 8 hours while under continuous vibration from a 6 pound air hammer. Breakout torque was increased until six times the 3,300 ft-lb makeup torque finally broke the joint.

High Lubricity - Tests were made using BAKERLOK on one side of a standard coupling and API Modified Thread Dope on the other. Identical pin threads were made up into the coupling. For the same amount of torque, the joint with BAKERLOK made up further and was cooler than the joint lubricated with standard thread dope. BAKERLOK has a 1.18 Friction Factor/Torque Factor.

Leak proof Seal - Joints made up with BAKERLOK using standard torque were tested with water pressures in excess of the listed burst pressure of the casing. The joint showed no leakage.

Corrosion Resistant - Five different samples of BAKERLOK covered steel and underwent a 96 hour ASTM and salt spray test. The result: no visible change in BAKERLOK; no acceleration of the normal corrosion rate on the five samples of steel.

Storage - Store in a cool, dry area in original or equivalent container in accordance with all regulations. Do not expose to extreme heat or flame. Do not expose to extreme cold. Store at 5 – 40°C, away from strong oxidizers and acids. The shelf life for BAKERLOK is 2 years from date of manufacture.

Emergency Release

In case of emergency, BAKERLOK can be released by heating the joint from 500° to 600° F and applying breakout torque immediately.

Coverage

Casing OD (in.)	Number of joints each Forumlok kit will lock
4-1/2	10
5-1/2	6
6-5/8 or 7	4
7-5/8, 8-5/8 or 9 5/8	3
10-3/4, 11 3/4 or 13-3/8	2
16 or 20	1